Alloy 600

Smiths Advanced Metals

Rev: SAM/datasheets/high-temperature-sheet/alloy-600/feb-2022

Nickel Chromium Sheet.

Non-magnetic sheet available ex-stock which we guillotine in-house

Alloy 600 offers excellent corrosion resistance with superior oxidation resistance and high carburisation resistance at high temperatures.

The material is virtually immune to the effects of chloride-induced stress corrosion cracking, a type of intergranular corrosion. This type of intergranular corrosion is common in austenitic stainless steel. Alloy 600 also performs well in high-temperature nitriding environments. The material combines high strength with good workability and is also readily weldable. Cold formability characteristics are similar when compared to chromium-nickel stainless steels.

Alloy 600 finds typical use in aerospace, chemical processing, food processing and power generation, including nuclear power.

We stock Alloy 600 sheets in various sizes, which we process in-house using our guillotining service.



Grades / Specifications

- AMS5540
- ASME B168
- **ASTM B168**

BS 3072

- NACE MR0175 UNS N06600, NA14,
- NiCr15Fe

Benefits

- Good corrosion resistance
- **Excellent** mechanical properties
- Good heat resistance
- Good workabilty

*Che	mical Co	ompositi	on (we	ght %)												
	Ni	Cr	Cu	С	Mn	Si	S	Fe	Р	Со	Nb	Ti	Та	AI	Cu	
min.	72.00	14.00						6.00								
max.		17.00	0.50	0.15	1.00	0.50	0.015	10.00	0.040	1.00	1.00	0.50	0.05	0.35	0.50	

* As per AMS 5540

Mechanical Properties								
	21°C	538°C	649°C	760°C	871°C	982°C	1093°C	
Ultimate Tensile Strength /MPa	641.2	579.2	448.2	189.6	103.4	51.7	-	
0.2% Yield Strength /MPa	255.1	196.5	182.7	117.2	62	27.6	-	
Elongation %	61	63.7	52.9	62.4	108.5	160	-	
Coefficient of Thermal Expansion µm/mºC	-	15.1	15.5	15.6	16.4	-	16.7	
Thermal Conductivity /kcal/(hr.m.°C)	12.8	19.6	21.3	19.3	23.8	-	-	
Modulus of Elasticity / x10 ⁵ MPa	2.1	1.77	1.69	1.63	1.53	-	1.4	

www.smithsadvanced.com



Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB

Tel: +44 (0) 1767 604710

info@smithsadvanced.com



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.



Page: 1 of 1