# **NES 833**

Smiths Advanced Metals

Rev: SAM/datasheets/bronze/nes-833-bar/feb-2022

## Nickel Aluminium Bronze Bar

For excellent corrosion resistance

#### NES 833 is a nickel aluminium bronze known for excellent corrosion resistance, high wear resistance and high galling resistance.

Other alloy features include high levels of toughness, strength and excellent performance characteristics at sub-zero temperatures. Corrosion resistance in both corrosion and erosion environments is outstanding. The material is produced to the specific requirements of the Ministry of Defence for Naval applications.

We also supply NES 833 bronze bars with a diameter greater than 15mm with ultrasonic inspection complying with DEF STAN 02-729 PT5. Impact values are also taken on all sizes above 15mm diameter.


Bars of grade NES 833 are available in various sizes from stock.

#### Grades / Specifications

2.9066	DEF STAN 02-833	
CA 104	DGS1043	
CuAl9Ni5Fe4	DGS8452	
CW207C	NE 451 116	

CW307G





### **Key Applications**

- Valve and pump components
- **Propeller shafts**
- **High-performance fasteners**
- Heavy duty bushes and bearings

Chemical Composition (weight %)											
	Cu	Al	Ni	Fe	Mn	Zn	Pb	Sn	Si	Mg	Total Impurities
min.	Bal	8.50	4.50	4.00							
max.	Bal	10.00	5.50	5.00	0.50	0.40	0.05	0.10	0.10	0.05	0.50

As per DEF STAN 02-833

Mechanical Properties									
Diameter	6-15mm	15-25mm	25-100mm	>100mm					
UTS	680 N/mm <sup>2</sup>	680 N/mm <sup>2</sup>	635 N/mm <sup>2</sup>	620 N/mm <sup>2</sup>					
Proof Strength	325 N/mm <sup>2</sup>	325 N/mm <sup>2</sup>	295 N/mm <sup>2</sup>	245 N/mm <sup>2</sup>					
Elongation	17%	17%	17%	15%					
Izod	-	24J	27J	23J					

Properties as per DEF STAN 02-833

#### **Technical Sales Assistance**

To find out more about the NES 833 aluminium bronze bars and for other technical advice, contact Smiths Advanced Metals today. Our team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Advanced Metals 2023



Page: 1 of 1